## METHOD FOR LOCALLY FORMING DIFFERENT BAND GAP IN QUANTUM WELL BY DIELECTRIC-SEMICONDUCTOR COMPOSITE COVER LAYER

Publication number: KR20010036949 (A)

Publication date: 2001-05-07 Inventor(s): CHOI WON

CHOI WON JUN [KR]; HAN IL GI [KR]; KANG GWANG NAM [KR]; KIM HOE JONG [KR]; KIM SEON HO [KR]; LEE HUI TAEK [KR]; LEE SEOK [KR]; WOO DEOK HA

[KR]; KIM SEON HO [KR]; LEE HUI TAEK [KR]; LEE SEOK [KR]; WOO DEOK H [KR] +

Applicant(s): KOREA INST SCIENCE TECHNOLOGY [KR] +

Classification:
- international: H01L21/18; H01L21/02; (IPC1-7); H01L21/18

- European: Application number: KR19990044158 19991012 Priority number(s): KR19990044158 19991012

## Abstract of KR 20010036949 (A)

PURPOSE: A method for locally forming a different band gap in a quantum well by a delectricsemiconductor composite cover layer is provided to regulate a degree of disactor of the quantum well. CONSTITUTION: The method begins with growing an inCasAsinGaAsP quantum well substrate by a chemical beam egitary technique. Not, a dielectric thin layer made of subst. a SiC2 or Sikt is called as a cover layer on the quantum well substrate by a plasma-enhanced chemical deposition technique. After a heat treatment steps is carried out at a temperature of 600. 800(deg), Cor 4-1 5 minute, the dielectric thin layer is removed. In addition, InP, InGaAs or InGaAsP is used as a semiconductor cover layer.

Data supplied from the espacenet database - Worldwide